# PVB varnish 60

Universal varnish for printed circuit boards. A quick-drying transparent PVB coat with good isolation properties. Protects printed circuit boards and other elements operating in unfavourable weather conditions from corrosion. The coating protects printed circuit boards against the creation of stray currents and short circuits.

Physicochemical properties			
State of matter	liquid		
Color	transparent		
Odor	characteristic		
Density at 20°C	~0,80 g/cm³		
Viscosity at 20°C	~50 cP		
Drying time	40-45 min		
Operating temperature	-50°C to 150°C		

## **Application:**

- Insulates and secures broadly understood electronics, printed boards, cables and wires, high-voltage transformers, electric motor coils;
- Used to avoid short-circuits in the automotive industry;
- Plastic seals of plug and socket casings;
- Creates protective layers in power engineering and electromechanics.

#### **Properties:**

Creates a protective and insulating layer that protects against weather influences such as moisture, oxidation, dusts, chemical contaminations; Adheres well to metal, plastic and wood surfaces; Creates a coating resistant to diluted acids, alkalis, and atmospheric agents; It is possible to solder through the varnish layer. Prevents sparks and corona discharge; Limits ground failures between paths. It does not change the transparency and elasticity even after a long time; Application temperature range: from -40°C to 60°C. Flash point: 380°C.

#### **Efficiency:**

50 ml	appro. 0,25 m²	
1 L	approx. 5 m <sup>2</sup>	

### Packagings:

Volume	Type of packaging	Collective packaging	Item Code
50 ml	plastic bottle with a brush	8	ART.AGT-199
1 L	metal canister	10	ART.AGT-217

#### Warehousing:

Keep away from sources of heat, hot surfaces, sparks, open flames and other sources of ignition. Protect from sunlight. Do not expose to temperatures exceeding 50°C/122°F.

Data contained in this document are consistent with the current state of our knowledge. They describe typical product properties and applications. However, it is up to the user to examine the suitability of this product for specific applications. We deny liability for the obtained results on the grounds that application conditions lie beyond our control.